

Classifications

EN ISO 17633-A	EN ISO 17633-B	AWS A5.22
T 19 9 L R M21 3	TS308L-F M21 0	E308LT0-1
T 19 9 L R C1 3	TS308L-F C1 0	E308LT0-4

Characteristics and typical fields of application

Rutile strip alloyed flux cored welding wire of type T 19 9 L R / E308LT0 for GMAW of stainless steels like 1.4306 / 304L. This product achieves high productivity and is easy to operate providing excellent operating characteristics, self-releasing slag, almost no spatter formation and temper discoloration, smooth weld finish and safe penetration. Increased travel speeds as well as little demand for cleaning and pickling provide considerable savings in time and money. Suitable for service temperatures from -196°C to +350°C. BÖHLER EAS 2-FD \varnothing 0.9 mm is well suitable for welding of sheet metal from 1.5 mm and \varnothing 1.2 mm can be used for wall thicknesses from 3 mm upwards. Wire \varnothing 0.9 mm is designed for positional welding, wire \varnothing 1.2 mm and 1.6 mm are recommended mainly for downhand and horizontal welding positions as well as in position PC/2G and slightly vertical down.

Base materials

1.4306 X2CrNi19-11, 1.4301 X5CrNi18-10, 1.4311 X2CrNiN18-10, 1.4312 GX10CrNi18-8, 1.4541 X6CrNiTi18-10, 1.4546 X5CrNiNb18-10, 1.4550 X6CrNiNb18-10
AISI 304, 304L, 304LN, 302, 321, 347; ASTM A157 Gr. C9, A320 Gr. B8C or D

Typical analysis of all-weld metal (wt.-%)


	C	Si	Mn	Cr	Ni
wt.-%	0.03	0.7	1.5	19.8	10.5

Mechanical properties of all-weld metal

Condition	Yield strength $R_{p2.0}$	Tensile strength R_m	Elongation A ($L_0=5d_0$)	Impact work ISO-V KV J	
	MPa	MPa	%	+20 °C	-196 °C
u	380 (≥ 320)	560 (≥ 520)	40 (≥ 35)	60	≥ 32

u untreated, as welded – (Argon + 15 – 25 % CO₂; 100 % CO₂)

Operating data

	Polarity: DC (+)	Shielding gases: M1 – M3; C1	Redrying: possible 150 °C / 24 h	\varnothing (mm)	Amps A	voltage V
				0.9	100 – 160	21 – 30
				1.2	125 – 280	20 – 34
1.6	200 – 350	25 – 35				

Welding with standard GMAW-facilities possible, slightly trailing torch position (angel appr. 80°), when using Argon + 15 – 25 % CO₂ as shielding gas it is necessary to decrease the voltage by 2 V; the gas flow should be 15 – 18 l/min

Approvals

TÜV-D (5348.), DB (43.014.14), CWB (E308LT0-1(4)), GL (4550 (C1, M21)), SEPROZ, CE