

Classifications		
EN ISO 18275-A	AWS A5.5	AWS A5.5M
E 62 5 Z2Ni B 4 5	E10018-G	E6918-G
	E10045-P2 (mod.)	E6945-P2 (mod.)

Characteristics and typical fields of application

Basic coated electrodes for vertical-down welds of large diameter pipelines and for structural work. Suitable for filler and cover pass welding in pipeline construction. Deposit is extremely crack resistant, and features high toughness and a very low hydrogen content. Special design and development work has enabled this electrode to provide exceptional striking characteristics and the avoidance of start porosity on cover (cap) passes. Due to this and the good welding characteristics this special basic electrode offers easy handling even under field conditions. Deposition rate is 80 – 100 % higher than for vertical up welding.

Base materials

L555MB
API Spec. 5 L: X80


Typical analysis of all-weld metal (wt.-%)

	C	Si	Mn	Ni
wt-%	0.07	0.4	1.2	2.3

Mechanical properties of all-weld metal

Condition	Yield strength R _e	Tensile strength R _m	Elongation A (L ₀ =5d ₀)	Impact work ISO-V KV J			
	MPa	MPa	%	+20 °C	±0 °C	-20 °C	-50 °C
u	670 (≥ 620)	730 (690 – 890)	24 (≥ 18)	150	125	120	70 (≥ 47)
u	untreated, as welded						

Operating data

	Polarity:	Redrying if necessary:	Electrode identification:	∅ (mm)	L mm	Amps A
		DC (+)	300 – 350 °C / min. 2 h	FOX BVD 100 10018-G E 62 5 Z2Ni B	4.0 4.5	350 350

Recommended interpass temperature > 100°C

Approvals

TÜV (06333.), SEPROZ, CE