

FONTARGEN A 200 L 58

Copper brazing alloy



ISO 17672:	Cu 110
DIN EN 1044:	CU 101
DIN 8513:	L-Cu
EN ISO 3677:	B-Cu100-1085
DIN EN 17933-52:	Cu-ETP
Material-no.:	2.0065 / 2.0060

Composition, typical analysis (% w/w):

Cu	P
> 99.9 (oxygenic)	< 0.025

Mechanical and physical properties:

Working temperature:	1100 °C
Melting range:	1083 °C (Eutectic)
Specific gravity:	8.9 g/cm ³
Tensile strength:	200 N/mm
Electrical conductivity:	56 - 58 Sm/mm ²

Characteristics / Applications:

Alloy suitable for gap brazing subjected to tough conditions. High-temperature brazing of alloyed and unalloyed steel.

Heat sources:

Inert-gas furnace, induction

Availability:

Bare rods	Coated rods	Wire	Foil	Preforms	Powder	Paste
<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

10/13/JL/1