

FONTARGEN A 331

Silver brazing alloy, cadmium-free



ISO 17672:	Ag 225
DIN EN 1044:	AG 205
DIN 8513:	L-Ag25
EN ISO 3677:	B-Cu40ZnAg-700/790

Composition, typical analysis (% w/w):

Ag	Cu	Zn
25	40	35

Mechanical and physical properties:

Working temperature:	780 °C
Melting range:	700 - 790 °C
Specific gravity:	8.8 g/cm ³
Tensile strength:	380 - 430 N/mm ²
Elongation:	25 %

Characteristics / Applications:

Silver alloy, cadmium free, insensitive to overheating. Gap brazing of alloyed and unalloyed steel, nickel and nickel alloys, malleable cast iron, copper and copper alloys. Good colour match with brass. Joint-brazing at working temperatures of max. 300 °C.

Heat sources:

Acetylene torch, induction and resistance heating

Flux:

F 300 - Series

Availability:

Bare rods	Coated rods	Wire	Foil	Preforms	Powder	Paste
<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

13/10/JL/1