

## Classifications

<b>EN ISO 18273</b>	<b>AWS A5.10</b>
S Al 4047A (AlSi12(A))	ER4047

## Characteristics and typical fields of application

Is used for aluminium-silicon casting alloy with a Si-content up to 12 %. Good flowing Al-alloy. Not suited for eloxal materials because of discoloration of the weld metal.

## Base materials

G-AlSi12	3.2581
G-AlSi10Mg(Cu)	3.2383
G-AlSi5Mg	3.2373

## Typical analysis of solid wire (wt.-%)

	Al	Si	Mn	Fe	Cu
wt.-%	bal.	12.0	< 0.15	< 0.6	< 0.3

## Mechanical properties of all-weld metal

Condition	Yield strength $R_{p0.2}$	Tensile strength $R_m$	Elongation A ( $L_0=5d_0$ )
	MPa	MPa	%
u	≥ 60	≥ 130	≥ 5
u	untreated, as welded		

## Operating data

	<b>Polarity:</b> AC	<b>Shielding gases:</b> (EN ISO 14175) I1	<b>ø (mm)</b> 1.6 2.0 2.4
---	------------------------	---	------------------------------------

Base material should be cleaned near the seam. Pre-heating 150 °C for plates > 15 mm

## Approvals

-